

## FABRENE® LC-30

### FABRIC SPECIFICATIONS

Weave: Woven Black HDPE scrim

Coating: 2 mil average each side  
(50 g/m<sup>2</sup> per side)

Color: Black or Colored coatings  
Available

Cores: 3, 4, 5 or 6 inch ID available

Width: Up to 144"

Length: Up to 1000 linear yards/roll

### PRODUCT PROPERTIES<sup>1</sup>

|  |   |                             |
|--|---|-----------------------------|
| Unit Weight<br>ASTM 3776                               | 13.4 oz/yd <sup>2</sup> (454 g/m <sup>2</sup> ) |                             |
| Thickness <sup>2</sup><br>ASTM D5199                   | 30 mil (762 µm)                                 |                             |
|  | <b>WARP</b>                                     | <b>WEFT</b>                 |
| Grab Strength<br>ASTM D751-00                          | 547 lb <sub>f</sub> (2435N)                     | 534 lb <sub>f</sub> (2375N) |
| Tongue Tear<br>ASTM D751-00                            | 80 lb <sub>f</sub> (355N)                       | 99 lb <sub>f</sub> (440N)   |
| Trapezoidal Tear<br>ASTM D751-00                       | 85lb <sub>f</sub> (380N)                        | 96 lb <sub>f</sub> (425N)   |
| Puncture Resistance<br>ASTM D4833                      | 280 lb <sub>f</sub> (1245N)                     |                             |
| Hydrostatic Resistance<br>ASTM D751-00                 | 480 psi (3310 kPa)                              |                             |
| Mullen Burst<br>ASTM D3786                             | 775 psi (5345 kPa)                              |                             |
| Volatile Loss<br>ASTM D1203                            | 0.04 %  |                             |
| Low Temperature Flex<br>ASTM D2136                     | Warp/Weft: Pass @ -30°C (-22°F)                 |                             |
| Dimensional Stability<br>ASTM D1204                    | Warp -1.7% Weft:-1.5%                           |                             |
| WVTR<br>ASTM E96                                       | 0.14 g/m <sup>2</sup> ·24 hrs                   |                             |
| Accelerated UV<br>Weathering <sup>3</sup><br>ASTM G154 | >90% strength retention after 2000 hrs          |                             |

<sup>1</sup> Data represents nominal values based on ASTM standard tests and should not be considered as limiting specifications.

<sup>2</sup> Nominal Value +/- 10%

<sup>3</sup> QUV (A-340 lamps)  
8 hrs UV @ 60°C; 4 hrs condensation @ 50°C

#### SALES INQUIRIES

Fabrene Inc  
Tel: (888) 322-7363 ext 234  
Tel: (705) 476-7057 ext 234  
Fax: (705) 476-7787

#### ORDER DESK

North Bay, Ontario, Canada  
Tel: (888) FABRENE  
(888) 322-7363  
ext 222 or 226  
Fax: (705) 476-0665

#### MAILING ADDRESS

Fabrene Inc  
240 Dupont Road  
P.O. Box 4040  
North Bay, Ontario, Canada  
P1B 9B4

