

FABRENE® AIR-GARD® VALUE

Made from polypropylene tapes, coated on one side with UV polypropylene and perforated.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		1.9	ASTM D3776
Warp Construction	Tapes/in	Warp	9.1	ASTM D3775
		Weft	3.3	
Widths	in		108	
1" Tensile Strength	lbf	Warp	59	ASTM D882
		Weft	31	
Dry Break Force	lbf	Warp	78	ASTM D5034
Dry Break Force	lbf	Weft	43	ASTM D5034
Coating	mil	White	.9	ASTM D1777 MOD
Scrim Colour		Natural		
Housewrap			PASS	
Water Vapour Transmission	g/100in ² /24hrs		2.6	ASTM E96 Proc A
Vapour Permeance	Perms		5	ASTM E-96 Proc. A
Low Temperature Bend	131°F		PASS	ASTM D2136
Water Resistance	hours		PASS	ASTM D-779
Nominal Thickness	mil		5	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® AIR-GARD® Value contains ultraviolet inhibitors but is not designed for extended outdoor exposure. For further information, contact your FABRENE Inc. representative. Air-Gard® Value is ICC certified (ESR - 2443)

Housewrap

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

