

FABRENE® CTSRW2E1

Made from high density polyethylene tapes, coated with low density polyethylene.
This product contains a multi metal VCI.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		2.9	ASTM D3776
Warp Construction	Tapes/in	Warp	8.1	ASTM D3775
	Tapes/in	Weft	8.1	
Widths	in		up to 120	
Tensile Grab Strength	lbf		Warp 101	ASTM D751
	lbf		Weft 67	
Tear Strength * (tongue)	lbf		Warp 49	ASTM D2261
	lbf		Weft 27	
Tear Strength (trapezoid)	lbf		Warp 62	ASTM D4533/D4851
	lbf		Weft 28	
Scrim Colour			Natural	
Coating	mil		Light Blue 1.2	ASTM D1777 MOD
	mil		White 1.2	
Thickness	mil		6	Caliper

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® CTSRW2E1 contains some ultraviolet inhibitors but is not recommended for extended outdoor exposure. The values presented on this datasheet are subject to change. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Anti-corrosion applications.

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

