

FABRENE® PIXEL™ 20 PE MEDIA

A light weight, billboard grade PE reinforced media fabric.
UV-Ready

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		2.7	ASTM D3776
Warp Construction	Tapes/in	Warp	9.1	ASTM D3775
	Tapes/in	Weft	3.3	
Widths	in		up to 150	
Tensile Grab Strength	lbf	Warp	70	ASTM D751
	lbf	Weft	70	
Tear Strength (trapezoid)	lbf	Warp	27	ASTM D4533/D4851
	lbf	Weft	27	
Coating	mil	Silver	.8	ASTM D1777 MOD
	mil	White	.8	
Thickness	mil		4	Caliper

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® PIXEL™ 20 PE Media contains some ultraviolet inhibitors and is designed for a 6-month outdoor exposure. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Media substrate

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

