

FABRENE® Q315WW

Made from high density polyethylene tapes, coated on two sides with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		12.1	ASTM D3776
Warp Construction	Tapes/in	Warp	16	ASTM D3775
	Tapes/in	Weft	16	
1" Tensile Strength	Lbf/inch	Warp	260	ASTM D4851
	Lbf/inch	Weft	255	
Tear Strength (trapezoid)	lbf	Warp	81	ASTM D4533/D4851
	lbf	Weft	78	
Coating Thickness	mil	White	3.5	ASTM D1777 Mod
	mil	White	3.5	
Coating Adhesion	lbf	Higher than	5	ASTM D4851
Modulus of Elasticity (warp) (/width)	lbf/ft	Warp	25.4	ASTM D4851
	lbf/ft	Weft	20.6	
Mullen Burst Strength	psi		661	ASTM D751
Low Temperature Bend	°-40 F		Pass	ASTM D2136
Flammability			Class A	ASTM E84-94
Light Transmission	%		16	
Thickness	mil		24	Caliper

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® Q315 contains ultraviolet inhibitors and is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Shelter fabric, Heavy tarpaulins.

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 17/08/03

SALES INQUIRIES

Fabrene Inc.
Tel:(888) 322-7363 ext 57250
Tel:(705) 476-7057 ext 57250
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 57222 or 57226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

