

FABRENE®

INDUSTRIAL SYNTHETIC FABRICS

TYPE RTGSW9W9

Made from high density polyethylene tapes, coated on two sides with low density polyethylene and FR additives.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		10.6	ASTM D3776
Warp Construction	Tapes/in	Warp	16	ASTM D3775
		Weft	16	
Tensile Grab Strength	lbf	Warp	354	ASTM D751
		Weft	348	
Tear Strength * (tongue)	lbf	Warp	118	ASTM D2261
		Weft	116	
Scrim Colour			Natural	
Coating	mil	White	2.9	ASTM D1777 MOD
	mil	White	2.9	
Nominal Thickness	mil		20.6	ASTM D1777 MOD
Flammability S102.2			PASS	CAN/ULC-S102.2
Flammability			PASS	NFPA 701 L
Flammability			PASS	CAN/ULC-S109-03 L
Flammability			PASS	CAN/ULC-S102
Light Transmission	%		16	
Fammability			PASS	NFPA 701-04 Method 2

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® RTGSW9W9 contains ultraviolet inhibitors and is suitable for outdoor applications.
For further information, contact your FABRENE Inc. representative.

Suggested Applications: Shelter fabric, Heavy tarpaulins where a degree of fire resistance is required.

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 08/02/01

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

