

FABRENE® STGSW7W7

Made from high density polyethylene tapes, coated on two sides with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		10.5	ASTM D3776
Warp Construction	Tapes/in	Warp	16	ASTM D3775
	Tapes/in	Weft	16	
Tensile Grab Strength	lbf	Warp	360	ASTM D751
	lbf	Weft	360	
Tear Strength * (tongue)	lbf	Warp	112	ASTM D2261
	lbf	Weft	112	
Tear Strength (trapezoid)	lbf	Warp	99	ASTM D4533/D4851
	lbf		81	
Scrim Colour			Natural	
Coating	mil	White	3	ASTM D1777 MOD
	mil	White	3	
Flammability				ASTM E84-94
Light Transmission	%		19	
Mullen Burst Strength	psi		551	ASTM D751
Nominal Thickness	mil		20	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® STGSW7W7 coatings contain ultraviolet inhibitors and is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Shelter fabric, Heavy tarpaulins.

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

