

FABRENE® T712W8F8

Made from high density polyethylene tapes, Multi pass coated on two sides with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		12	ASTM D3776
Warp Construction	Tapes/in	Warp	16	ASTM D3775
	Tapes/in	Weft	16	
Tensile Grab Strength	lbf	Warp	382	ASTM D751
	lbf	Weft	376	
Tear Strength * (tongue)	lbf	Warp	90	ASTM D2261
	lbf	Weft	70	
Tear Strength (trapezoid)	lbf	Warp	N/A	ASTM D4533/D4851
	lbf	Weft	N/A	
Scrim Colour			Black	
Coating	mil	BlackGreen	5.7	ASTM D1777 MOD
	mil	White	2.6	
Coating	mil			ASTM D1777 MOD
Mullen Burst Strength	psi		602	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® T712W8F8 contains ultraviolet inhibitors and are suitable for outdoor applications.
 For further information, contact your FABRENE Inc. representative.
 S706 is a development product. Physical properties could change slightly.

Suggested Applications: Shelter fabric, Heavy tarpaulins.

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

