

FABRENE®

INDUSTRIAL SYNTHETIC FABRICS

TYPE TSRB1W2 LUMBERWRAP

HD polyethylene scrim that has been coated on two sides with LD polyethylene

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		2.9	ASTM D3776
Warp Construction	Tapes/in	Warp	8	ASTM D3775
		Weft	8	
Widths	in	up to	120	
Tensile Grab Strength	lbf	Warp	90	ASTM D751
		Weft	98	
Tear Strength * (tongue)	lbf	Warp	41	ASTM D2261
		Weft	44	
Tear Strength (trapezoid)	lbf	Warp	25	ASTM D4533
		Weft	22	
Coating Thickness	mil	White	.9	ASTM D1777 MOD
	mil	Black	1	
Mullen Burst Strength	psi		129	ASTM D751
Nominal Thickness	mil		4.1	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® TSR Lumberwrap contains some UV inhibitors and is suitable for short-term outdoor applications.
For further information, contact your FABRENE Inc. representative.

Suggested Applications: Lumber covers

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 01/05/10

SALES INQUIRIES

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

