

FABRENE® VIIIE9

Made from high density polyethylene tapes and coated on one side with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd ²		2.5	ASTM D3776
Warp Construction	Tapes/in	Warp	9.1	ASTM D3775
	Tapes/in	Weft	8.1	
Widths	in	up to	150	
Tensile Grab Strength	lbf	Warp	105	ASTM D751
	lbf	Weft	110	
Tear Strength * (tongue)	lbf	Warp	NA	ASTM D2261
	lbf	Weft	NA	
Tear Strength (trapezoid)	lbf	Warp	NA	ASTM D4533/D4851
	lbf	Weft	NA	
Coating Thickness	mil	Light Blue	.7	ASTM D1777 Mod
Mullen Burst Strength	psi		NA	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® VIIIE9 contains ultraviolet inhibitors and is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Protective Membrane Roofing Systems

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

SALES INQUIRIES

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

ORDER DESK

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

MAILING ADDRESS

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

