

### FABRENE® W147N6N6

HDPE tapes, coated on both sides with high UV stabilized LDPE coating.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	oz/yd <sup>2</sup>		5.8	ASTM D3776
Warp Construction	Tapes/in	Warp	8.1	ASTM D3775
	Tapes/in	Weft	5.3	
Widths	in		up to 144	
Tensile Grab Strength	lbf		Warp 207	ASTM D751
	lbf		Weft 157	
Tear Strength * (tongue)	lbf		Warp 62	ASTM D2261
	lbf		Weft 67	
Coating	mil		Natural 2.1	ASTM D1777 MOD
	mil		Natural 2.1	

\* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® W147N6N6 is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Shelters, outdoor covers

NOTE: These values are typical data and are not intended as limiting specifications.

Date: 15/09/30

#### SALES INQUIRIES

**Fabrene Inc.**  
 Tel: (888) 322-7363 ext 234  
 Tel: (705) 476-7057 ext 234  
 Fax: (705) 476-7787

#### ORDER DESK

**North Bay, ON, Canada**  
 Tel: (888) FABRENE  
 (888) 322-7363  
 ext. 222 or 226  
 Fax: (705) 476-0665

#### MAILING ADDRESS

**Fabrene Inc.**  
 240 Dupont Rd.  
 P.O. Box 4040  
 North Bay, ON, Canada  
 P1B 9B4

