

FABRENE® AIR-GARD® VALUE

Made from polypropylene tapes, coated on one side with UV polypropylene and perforated.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		66	ASTM D3776
Warp Construction	Tapes/10cm	Warp	36	ASTM D3775
	Tapes/10cm	Weft	13	
Widths	mm		2745	
1" Tensile Strength	Newton	Warp	262	ASTM D882
	Newton	Weft	138	
Dry Break Force	Newton	Warp	345	ASTM D5034
Dry Break Force	Newton	Weft	192.5	ASTM D5034
Coating	µm	White	23	ASTM D1777 MOD
Scrim Colour		Natural		
Housewrap			PASS	
Water Vapour Transmission	g/m ² /24hrs		40.2	ASTM E96 Proc A
Vapour Permeance	Perms		5.1	ASTM E-96 Proc. A
Low Temperature Bend	55°C		PASS	ASTM D2136
Water Resistance	hours		PASS	ASTM D-779
Nominal Thickness	µm		127	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® AIR-GARD® Value contains ultraviolet inhibitors but is not designed for extended outdoor exposure.
 For further information, contact your FABRENE Inc. representative.
 Air-Gard® Value is ICC certified (ESR - 2443)

Housewrap

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

