

FABRENE® CTSRW2E1

Made from high density polyethylene tapes, coated with low density polyethylene.
This product contains a multi metal VCI.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		100	ASTM D3776
Warp Construction	Tapes/10cm	Warp	32	ASTM D3775
	Tapes/10cm	Weft	32	
Widths	mm		up to 3050	
Tensile Grab Strength	Newtons		Warp 450	ASTM D751
	Newtons		Weft 300	
Tear Strength * (tongue)	Newtons		Warp 220	ASTM D2261
	Newtons		Weft 120	
Tear Strength (trapezoid)	Newtons		Warp 275	ASTM D4533/D4851
	Newtons		Weft 123	
Scrim Colour			Natural	
Coating	µm	Light Blue	31.5	ASTM D1777 MOD
	µm	White	31.5	
Thickness	µm		152	Caliper

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® CTSRW2E1 contains some ultraviolet inhibitors but is not recommended for extended outdoor exposure.
The values presented on this datasheet are subject to change.
For further information, contact your FABRENE Inc. representative.

Suggested Applications: Anti-corrosion applications.

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

