

FABRENE® T712W8F8

Made from high density polyethylene tapes, Multi pass coated on two sides with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m2		405.3	ASTM D3776
Warp Construction	Tapes/10cm	Warp	63	ASTM D3775
	Tapes/10cm	Weft	63	
Tensile Grab Strength	Newton	Warp	1697	ASTM D751
	Newton	Weft	1671	
Tear Strength * (tongue)	Newton	Warp	402	ASTM D2261
	Newton	Weft	310	
Tear Strength (trapezoid)	Newton	Warp	N/A	ASTM D4533/D4851
	Newton	Weft	N/A	
Scrim Colour			Black	
Coating	µm	BlackGreen	144.9	ASTM D1777 MOD
	µm	White	65.6	
Coating	µm			ASTM D1777 MOD
Mullen Burst Strength	kPa		4150	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® T712W8F8 contains ultraviolet inhibitors and are suitable for outdoor applications.

For further information, contact your FABRENE Inc. representative.

S706 is a development product. Physical properties could change slightly.

Suggested Applications: Shelter fabric, Heavy tarpaulins.

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.

Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

North Bay, ON, Canada

Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

Fabrene Inc.

240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

