

FABRENE® TSRB1W2 LUMBERWRAP

HD polyethylene scrim that has been coated on two sides with LD polyethylene

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		99	ASTM D3776
Warp Construction	Tapes/10cm	Warp	31.5	ASTM D3775
	Tapes/10cm	Weft	31.4	
Widths	mm	up to	3050	
Tensile Grab Strength	Newton	Warp	400	ASTM D751
	Newton	Weft	438	
Tear Strength * (tongue)	Newton	Warp	183	ASTM D2261
	Newton	Weft	196	
Tear Strength (trapezoid)	Newton	Warp	110	ASTM D4533/D4851
	Newton	Weft	100	
Coating	µm	White	24	ASTM D1777 MOD
	µm	Black	26	
Mullen Burst Strength	kPa		889	ASTM D751
Nominal Thickness	µm		103	ASTM D1777 MOD

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® TSR Lumberwrap contains some UV inhibitors and is suitable for short-term outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Lumber covers

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4



ISO 9001:2008
 Certified
 Certificate 95610