

FABRENE® VIIIE9

Made from high density polyethylene tapes and coated on one side with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		86	ASTM D3776
Warp Construction	Tapes/10cm	Warp	36	ASTM D3775
	Tapes/10cm	Weft	32	
Widths	mm	up to	3810	
Tensile Grab Strength	Newton	Warp	465	ASTM D751
	Newton	Weft	490	
Tear Strength * (tongue)	Newton	Warp	NA	ASTM D2261
	Newton	Weft	NA	
Tear Strength (trapezoid)	Newton	Warp	NA	ASTM D4533/D4851
	Newton	Weft	NA	
Coating Thickness	µm	Light Blue	17	ASTM D1777 Mod
Mullen Burst Strength	kPa		NA	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® VIIIE9 contains ultraviolet inhibitors and is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Protective Membrane Roofing Systems

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.
 Tel: (888) 322-7363 ext 234
 Tel: (705) 476-7057 ext 234
 Fax: (705) 476-7787

North Bay, ON, Canada
 Tel: (888) FABRENE
 (888) 322-7363
 ext. 222 or 226
 Fax: (705) 476-0665

Fabrene Inc.
 240 Dupont Rd.
 P.O. Box 4040
 North Bay, ON, Canada
 P1B 9B4

