

## FABRENE® W147N6N6

HDPE tapes, coated on both sides with high UV stabilized LDPE coating.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m <sup>2</sup>		196	ASTM D3776
Warp Construction	Tapes/10cm	Warp	32	ASTM D3775
	Tapes/10cm	Weft	21	
Widths	mm		up to 3660	
Tensile Grab Strength	Newtons		Warp 920	ASTM D751
	Newtons		Weft 700	
Tear Strength * (tongue)	Newtons		Warp 275	ASTM D2261
	Newtons		Weft 300	
Coating	µm	Natural	54	ASTM D1777 MOD
	µm	Natural	54	

\* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® W147N6N6 is suitable for outdoor applications. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Shelters, outdoor covers

NOTE: These values are typical data and are not intended as limiting specifications.

### SALES INQUIRIES

### ORDER DESK

### MAILING ADDRESS

Date: 2015/09/30

**Fabrene Inc.**  
 Tel: (888) 322-7363 ext 234  
 Tel: (705) 476-7057 ext 234  
 Fax: (705) 476-7787

**North Bay, ON, Canada**  
 Tel: (888) FABRENE  
 (888) 322-7363  
 ext. 222 or 226  
 Fax: (705) 476-0665

**Fabrene Inc.**  
 240 Dupont Rd.  
 P.O. Box 4040  
 North Bay, ON, Canada  
 P1B 9B4

