

FABRENE® Y731N9N9

Made from high density polyethylene tapes, coated on both sides with low density polyethylene.
This product is UV stabilized and has Flame Resistance.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		237	ASTM D3776
Warp Construction	Tapes/10cm	Warp	48	ASTM D3775
	Tapes/10cm	Weft	32	
Widths	mm		up to 3660	
Tensile Grab Strength	Newtons		Warp 1200	ASTM D751
	Newtons		Weft 1100	
Tear Strength * (tongue)	Newtons		Warp 435	ASTM D2261
	Newtons		Weft 440	
Coating	µm	Natural	45	ASTM D1777 MOD
Mullen Burst Strength	kPa		2600	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® Y731N9N9 contains ultraviolet inhibitors and is suitable for prolonged outdoor exposure.
For further information, contact your FABRENE Inc. representative.

Suggested Applications: Covers

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES**ORDER DESK****MAILING ADDRESS**

Date: 2015/09/30

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

