

FABRENE® YCW1

Made from high density polyethylene tapes and coated on one side with low density polyethylene.

<u>PROPERTY</u>	<u>UNIT</u>		<u>VALUES</u>	<u>TEST METHOD</u>
Unit Weight	g/m ²		78	ASTM D3776
Warp Construction	Tapes/10cm	Warp	36	ASTM D3775
	Tapes/10cm	Weft	19	
Widths	mm	up to	1880	
Tensile Grab Strength	Newton	Warp	460	ASTM D751
	Newton	Weft	405	
Tear Strength * (tongue)	Newton	Warp	190	ASTM D2261
	Newton	Weft	210	
Tear Strength (trapezoid)	Newton	Warp	210	ASTM D4533/D4851
	Newton	Weft	180	
Scrim Colour			White	
Coating	µm		23.9	ASTM D1777 MOD
Mullen Burst Strength	kPa		NA	ASTM D751

* Includes force to shift tapes - Tear may be crosswise to direction of force.

Fabrene® YCW1 contains some ultraviolet inhibitors but is not recommended for prolonged outdoor exposure. For further information, contact your FABRENE Inc. representative.

Suggested Applications: Bale covers.

NOTE: These values are typical data and are not intended as limiting specifications.

SALES INQUIRIES

ORDER DESK

MAILING ADDRESS

Date: 2015/09/30

Fabrene Inc.
Tel: (888) 322-7363 ext 234
Tel: (705) 476-7057 ext 234
Fax: (705) 476-7787

North Bay, ON, Canada
Tel: (888) FABRENE
(888) 322-7363
ext. 222 or 226
Fax: (705) 476-0665

Fabrene Inc.
240 Dupont Rd.
P.O. Box 4040
North Bay, ON, Canada
P1B 9B4

